




Satin Plaster

Hand-applied top layer finish for
all indoor surfaces



Saint-Gobain Rigips
Alçı Sanayi ve Ticaret A.Ş.

İlkbahar Mahallesi, 606. Sokak No : 8
Çankaya 06550 Ankara
Tel : +90 312 463 63 63
www.rigips.com.tr



SATIN PLASTER

PREPARATION AND APPLICATION



In a clean bucket, add 10 kg of Rigips Satin Finishing Plaster gradually to 7 litres of water. Wait for a few minutes for the full contact of the material and water.



Mix with hand mixer or trowel until homogeneous.



The prepared mortar is applied to the wall with a steel trowel.



The thicknesses resulting from trowel passages are again corrected by pressing with a steel trowel. If a glossy surface is desired, a certain amount of mortar is applied.

IMPORTANT NOTES

- ▶ The application environment and surface temperature should be at least + 5°C.
- ▶ The container and equipment to be used during the mixing process must be clean in every use.
- ▶ In order not to create lumps, no water or plaster should be added to the mixture during and/or after mixing.
- ▶ Application surface should be free from dust, oil and dirt.
- ▶ Wait for the mortar to start hardening in order to remove the traces of the trowel formed during the application and trim the surface with the edge of the steel trowel.
- ▶ Considering the fineness of the Rigips Satin, trimming must be made with precision.

TECHNICAL PROPERTIES

Color	White and similar tones
Density	640 - 740 kg/m ³
Water / Plaster Ratio	7 / 10
Application Time	100 mins
Compression Strength	Minimum of 2,0 N/mm ²
Fire Reaction Class	A1
Packaging	
Type	Polypropylene Bag
Weight	25 kg ± 2%



STORAGE CONDITIONS



They should be stacked up to 20 bags on pallets and stored in a dry and cool environment protected against freezing.



Use within 6 months from date of manufacture.

HEALTH AND SAFETY



- ▶ Keep out of reach of children.
- ▶ Use helmet, goggles, glove and mask for your health and safety during applications.
- ▶ In case of eye contact, rinse immediately with plenty of water and seek medical advice.

